

EKAN® MIX 640

New generation superplasticizer with high workability and high water reduction. Recommended for summer climates.



Ready-Mix Concrete Admixtures
Hyperplasticizers



T 11.1 / T 11.2

CHARACTERISTICS

EKAN® MIX 640 is a new generation superplasticizing additive, formulated to ensure high water reduction and high workability.

It promotes the production of highly fluid concretes, with controlled rheology that facilitates placement and finishing. Ideal for pumped concrete or complex elements, it ensures stable consistency and excellent surface quality.

EKAN® MIX 640 is suitable for low temperatures. It extends the setting time of the concrete.

It must not be mixed or used together with naphthalene sulfonate-based additives.

INSTRUCTIONS FOR USE

Areas of use

- All types of cement (except aluminous cement)
- Ready-mixed concrete
- Reinforced concrete
- Mass concrete
- Pumped concrete

Application

Dosage: 0.4 kg – 2.0 kg per 100 kg of cement. For general concrete applications: 0.4% – 0.8%.

For high-fluidity or self-compacting concrete applications: 0.8% – 2.0%.

EKAN® MIX 640 is completely water-soluble. To achieve the best performance, it is recommended to add the product to the second half of the mixing water.

The optimal dosage of EKAN® MIX 640 should be determined after local testing of the desired mechanical properties of the cement and the workability of the mix.

TECHNICAL DATA


Appearance: Homogeneous

Color: Light brown

Density: 1.09 ± 0.03 kg/L

pH: 4.5 ± 1.0

CERTIFICATIONS



PRECAUTIONS

The shelf life of EKAN® MIX 640 is 12 months when stored in its original packaging in a dry environment protected from direct sunlight.

After a long period of inactivity, shake, stir the product, or use a circulation pump to homogenize it before use.

After a freeze/thaw cycle, stir the product before use.

Avoid contact with eyes and skin. Detailed health and safety information is available in the Material Safety Data Sheet (MSDS).